

NENIR04B - September 9, 2022

Item # NENIR04B was discontinued on September 9, 2022. For informational purposes, this is a copy of the website content at that time and is valid only for the stated product.

UNMOUNTED NIR ABSORPTIVE ND FILTERS

- ▶ Optimized for Attenuation at 1064 nm and 1550 nm
- ▶ Ø1/2", Ø25 mm, and 2" x 2" Versions Available
- ▶ Good Transmission Through Visible Range for Easy Beam Alignment
- ▶ Effective Heat Absorbing Filters



NENIR240B
2" x 2"



NENIR40B
Ø1"



NENIR506B
Ø1/2"




NENIR30B
in an LMR1
Mount

[Hide Overview](#)

OVERVIEW

Features

- Ø1/2", Ø25 mm, and 2" Square Unmounted Filters
- Design Wavelength: 1550 nm
- Optical Densities Ranging from 0.1 to 6.0
- Ideal for Low-Power Applications (<1 W; see the Specs Tab for Additional Details)
- Wavelength Range: 1000 - 2600 nm
- Good Visible Wavelength Transmission (See Graph to the Right)
- Absorptive Glass Reduces Multiple Reflections



Click to Enlarge



Thorlabs' unmounted near infrared absorptive neutral density filters have optical densities ranging from 0.1 to 6.0. These shortpass, heat-protective filters are designed to be transmissive in the visible region, allowing for passage of an alignment beam, and absorptive in the near infrared. Although optimized at 1550 nm, this optimization also leads to excellent performance at 1064 nm (see below for details). These filters have a relatively flat spectral response from 1000 nm - 1600 nm and are effective attenuators up to 2600 nm. They can also be used as heat absorbing filters, transmitting <2% above 4 µm. A selection of the Ø25 mm filters is also available in SM1-threaded mounts.

Each absorptive NIR ND filter is fabricated from one member of a family of Schott glasses (NG11, KG2, KG3, or KG5). Each Schott glass has a spectrally flat absorption coefficient from 1000 - 1600 nm. By varying the thickness of the glass, we are able to produce our entire line of NIR ND filters from just four types of Schott glass. Refer to the *Graphs* tab above for detailed information about the average transmission obtained with each of our absorptive neutral density filters. For applications that would benefit from reduced surface reflections, Thorlabs offers NIR absorptive ND filters with an AR coating for the 1050 - 1700 nm wavelength range.

The filters sold on this page are uncoated. For our full selection of coated and uncoated ND filters, please see the Selection Guide table on the right.

Optical Density and Transmission

Neutral Density Filter Selection Guide

Absorptive

Uncoated (400 - 650 nm)	Mounted
	Unmounted
Uncoated (1000 - 2600 nm)	Mounted
	Unmounted
AR Coated (350 - 700 nm)	Mounted
	Unmounted
AR Coated (650 - 1050 nm)	Mounted
	Unmounted
AR Coated (1050 - 1700 nm)	Mounted
	Unmounted

Variable

Reflective

UV Fused Silica (200 - 1200 nm)	Mounted
	Unmounted
N-BK7 (350 - 1100 nm)	Mounted
	Unmounted
ZnSe (2 - 16 µm)	Mounted
	Unmounted

Wedged UVFS

Optical density (OD) indicates the attenuation factor provided by an optical filter, i.e. how much it reduces the optical power of an incident beam. OD is related to the transmission, T , by the equation

$$OD = \log_{10} \left(\frac{1}{T} \right), \text{ or } T = 10^{-OD}$$

where T is a value between 0 and 1. Choosing an ND filter with a higher optical density will translate to lower transmission and greater absorption of the incident light. For higher transmission and less absorption, a lower optical density would be appropriate. As an example, if a filter with an OD of 2 results in a transmission value of 0.01, this means the filter attenuates the beam to 1% of the incident power. Please note that the transmission data for our neutral density filters is provided in percent (%).

Please note that these products are not designed for use as laser safety equipment. For lab safety, Thorlabs offers an extensive line of safety and blackout products, including beam blocks, that significantly reduce exposure to stray light.

(200 - 1200 nm)

Wedged N-BK7
(350 - 1100 nm)Wedged ZnSe
(2 - 16 μm)

Variable

Neutral Density Filter Kits[Hide Specs](#)**S P E C S**


ND Filter Size	$\varnothing 1/2"$ (12.7 mm)	$\varnothing 25.0$ mm	2" x 2"
Size Tolerance	+0.0 / -0.2 mm (Diameter)		+0.0 / -0.25 mm (H, L)
Clear Aperture	> $\varnothing 11.4$ mm	> $\varnothing 22.5$ mm	>45.72 mm x >45.72 mm
Surface Flatness	$\lambda/4$ @ 633 nm		2λ @ 633 nm
Design Wavelength	1550 nm		
Wavelength Range	1000 - 2600 nm		
Surface Quality	40-20 Scratch-Dig		
Parallelism	<10 arcsec		
Optical Density Tolerance	$\pm 5\%$ @ 1550 nm		

[Click here to download complete optical density and transmission data.](#)


Damage Threshold Specifications		
Optical Density	Damage Threshold	
1.0	Pulsed	8 J/cm ² (1064 nm, 10 ns, 10 Hz, $\varnothing 1.040$ mm) 20 J/cm ² (1542 nm, 10 ns, 10 Hz, $\varnothing 0.144$ mm)
	CW ^{a,b}	25 W/cm (1540 nm, $\varnothing 1.030$ mm)
3.0	CW ^{a,b}	25 W/cm (1064 nm, $\varnothing 0.062$ mm)
5.0	CW ^{a,b}	15 W/cm (1540 nm, $\varnothing 1.030$ mm)

- a. The power density of your beam should be calculated in terms of W/cm. For an explanation of why the linear power density provides the best metric for long pulse and CW sources, please see the *Damage Thresholds* tab.
- b. CW testing was performed using a 30 second exposure at each test site.

[Hide Graphs](#)**G R A P H S**



[Click to Enlarge](#)



[Click to Enlarge](#)

[Click here to download optical density and transmission data.](#)

For the transmission and optical density of a particular filter, please click the blue icon (📄) in the row corresponding to the filter in the tables below.

[Hide Damage Thresholds](#)

DAMAGE THRESHOLDS

Damage Threshold Data for Thorlabs' NIR Absorptive ND Filters

The specifications to the right are measured data for Thorlabs' NIR absorptive ND filters. Damage threshold specifications are constant for a given optical density, regardless of the size of the filter. CW testing for these filters was performed using a 30 second exposure at each test site.

Damage Threshold Specifications		
Optical Density	Damage Threshold	
1.0	Pulsed	8 J/cm ² (1064 nm, 10 ns, 10 Hz, Ø1.040 mm) 20 J/cm ² (1542 nm, 10 ns, 10 Hz, Ø0.144 mm)
	CW ^{a,b}	25 W/cm (1540 nm, Ø1.030 mm)
3.0	CW ^{a,b}	25 W/cm (1064 nm, Ø0.062 mm)
5.0	CW ^{a,b}	15 W/cm (1540 nm, Ø1.030 mm)

- The power density of your beam should be calculated in terms of W/cm. For an explanation of why the linear power density provides the best metric for long pulse and CW sources, please see the "Continuous Wave and Long-Pulse Lasers" section below.
- CW testing was performed using a 30 second exposure at each test site.

Laser Induced Damage Threshold Tutorial

The following is a general overview of how laser induced damage thresholds are measured and how the values may be utilized in determining the appropriateness of an optic for a given application. When choosing optics, it is important to understand the Laser Induced Damage Threshold (LIDT) of the optics being used. The LIDT for an optic greatly depends on the type of laser you are using. Continuous wave (CW) lasers typically cause damage from thermal effects (absorption either in the coating or in the substrate). Pulsed lasers, on the other hand, often strip electrons from the lattice structure of an optic before causing thermal damage. Note that the guideline presented here assumes room temperature operation and optics in new condition (i.e., within scratch-dig spec, surface free of contamination, etc.). Because dust or other particles on the surface of an optic can cause damage at lower thresholds, we recommend keeping surfaces clean and free of debris. For more information on cleaning optics, please see our [Optics Cleaning](#) tutorial.

Testing Method

Thorlabs' LIDT testing is done in compliance with ISO/DIS 11254 and ISO 21254 specifications.

First, a low-power/energy beam is directed to the optic under test. The optic is exposed in 10 locations to this laser beam for 30 seconds (CW) or for a number of pulses (pulse repetition frequency specified). After exposure, the optic is examined by a microscope (~100X magnification) for any visible damage. The number of locations that are damaged at a particular power/energy level is recorded. Next, the power/energy is either increased or decreased and the optic is exposed at 10 new locations. This process is repeated until damage is observed. The damage threshold is then assigned to be the highest power/energy that the optic can withstand without causing damage. A histogram such as that below represents the testing of one BB1-E02 mirror.



The photograph above is a protected aluminum-coated mirror after LIDT testing. In this particular test, it handled 0.43 J/cm^2 (1064 nm, 10 ns pulse, 10 Hz, $\text{Ø}1.000 \text{ mm}$) before damage.

According to the test, the damage threshold of the mirror was 2.00 J/cm^2 (532 nm, 10 ns pulse, 10 Hz, $\text{Ø}0.803 \text{ mm}$). Please keep in mind that these tests are performed on clean optics, as dirt and contamination can significantly lower the damage threshold of a component. While the test results are only representative of one coating run, Thorlabs specifies damage threshold values that account for coating variances.

Continuous Wave and Long-Pulse Lasers

When an optic is damaged by a continuous wave (CW) laser, it is usually due to the melting of the surface as a result of absorbing the laser's energy or damage to the optical coating (antireflection) [1]. Pulsed lasers with pulse lengths longer than $1 \mu\text{s}$ can be treated as CW lasers for LIDT discussions.

When pulse lengths are between 1 ns and $1 \mu\text{s}$, laser-induced damage can occur either because of absorption or a dielectric breakdown (therefore, a user must check both CW and pulsed LIDT). Absorption is either due to an intrinsic property of the optic or due to surface irregularities; thus LIDT values are only valid for optics meeting or exceeding the surface quality specifications given by a manufacturer. While many optics can handle high power CW lasers, cemented (e.g., achromatic doublets) or highly absorptive (e.g., ND filters) optics tend to have lower CW damage thresholds. These lower thresholds are due to absorption or scattering in the cement or metal coating.

Pulsed lasers with high pulse repetition frequencies (PRF) may behave similarly to CW beams. Unfortunately, this is highly dependent on factors such as absorption and thermal diffusivity, so there is no reliable method for determining when a high PRF laser will damage an optic due to thermal effects. For beams with a high PRF both the average and peak powers must be compared to the equivalent CW power. Additionally, for highly transparent materials, there is little to no drop in the LIDT with increasing PRF.

In order to use the specified CW damage threshold of an optic, it is necessary to know the following:


1. Wavelength of your laser
2. Beam diameter of your beam ($1/e^2$)
3. Approximate intensity profile of your beam (e.g., Gaussian)
4. Linear power density of your beam (total power divided by $1/e^2$ beam diameter)

Thorlabs expresses LIDT for CW lasers as a linear power density measured in W/cm. In this regime, the LIDT given as a linear power density can be applied to any beam diameter; one does not need to compute an adjusted LIDT to adjust for changes in spot size, as demonstrated by the graph to the right. Average linear power density can be calculated using the equation below.


$$\text{Linear Power Density} = \frac{\text{Power}}{\text{Beam Diameter}}$$

The calculation above assumes a uniform beam intensity profile. You must now consider hotspots in the beam or other non-uniform intensity profiles and roughly calculate a maximum power density. For reference, a Gaussian beam typically has a maximum power density that is twice that of the uniform beam (see lower right).


Now compare the maximum power density to that which is specified as the LIDT for the optic. If the optic was tested at a wavelength other than your operating wavelength, the damage threshold must be scaled appropriately. A good rule of thumb is that the damage threshold has a linear relationship with wavelength



Example Test Data			
Fluence	# of Tested Locations	Locations with Damage	Locations Without Damage
1.50 J/cm^2	10	0	10
1.75 J/cm^2	10	0	10
2.00 J/cm^2	10	0	10
2.25 J/cm^2	10	1	9
3.00 J/cm^2	10	1	9
5.00 J/cm^2	10	9	1



LIDT in linear power density vs. pulse length and spot size. For long pulses to CW, linear power density becomes a constant with spot size. This graph was obtained from [1].



such that as you move to shorter wavelengths, the damage threshold decreases (i.e., a LIDT of 10 W/cm at 1310 nm scales to 5 W/cm at 655 nm):

$$\text{Adjusted LIDT} = \text{LIDT Power} \left(\frac{\text{Your Wavelength}}{\text{LIDT Wavelength}} \right)$$

While this rule of thumb provides a general trend, it is not a quantitative analysis of LIDT vs wavelength. In CW applications, for instance, damage scales more strongly with absorption in the coating and substrate, which does not necessarily scale well with wavelength. While the above procedure provides a good rule of thumb for LIDT values, please contact Tech Support if your wavelength is different from the specified LIDT wavelength. If your power density is less than the adjusted LIDT of the optic, then the optic should work for your application.

Please note that we have a buffer built in between the specified damage thresholds online and the tests which we have done, which accommodates variation between batches. Upon request, we can provide individual test information and a testing certificate. The damage analysis will be carried out on a similar optic (customer's optic will not be damaged). Testing may result in additional costs or lead times. Contact Tech Support for more information.

Pulsed Lasers

As previously stated, pulsed lasers typically induce a different type of damage to the optic than CW lasers. Pulsed lasers often do not heat the optic enough to damage it; instead, pulsed lasers produce strong electric fields capable of inducing dielectric breakdown in the material. Unfortunately, it can be very difficult to compare the LIDT specification of an optic to your laser. There are multiple regimes in which a pulsed laser can damage an optic and this is based on the laser's pulse length. The highlighted columns in the table below outline the relevant pulse lengths for our specified LIDT values.

Pulses shorter than 10^{-9} s cannot be compared to our specified LIDT values with much reliability. In this ultra-short-pulse regime various mechanics, such as multiphoton-avalanche ionization, take over as the predominate damage mechanism [2]. In contrast, pulses between 10^{-7} s and 10^{-4} s may cause damage to an optic either because of dielectric breakdown or thermal effects. This means that both CW and pulsed damage thresholds must be compared to the laser beam to determine whether the optic is suitable for your application.

Pulse Duration	$t < 10^{-9}$ s	$10^{-9} < t < 10^{-7}$ s	$10^{-7} < t < 10^{-4}$ s	$t > 10^{-4}$ s
Damage Mechanism	Avalanche Ionization	Dielectric Breakdown	Dielectric Breakdown or Thermal	Thermal
Relevant Damage Specification	No Comparison (See Above)	Pulsed	Pulsed and CW	CW

When comparing an LIDT specified for a pulsed laser to your laser, it is essential to know the following:

1. Wavelength of your laser
2. Energy density of your beam (total energy divided by $1/e^2$ area)
3. Pulse length of your laser
4. Pulse repetition frequency (prf) of your laser
5. Beam diameter of your laser ($1/e^2$)
6. Approximate intensity profile of your beam (e.g., Gaussian)


The energy density of your beam should be calculated in terms of J/cm^2 . The graph to the right shows why expressing the LIDT as an energy density provides the best metric for short pulse sources. In this regime, the LIDT given as an energy density can be applied to any beam diameter; one does not need to compute an adjusted LIDT to adjust for changes in spot size. This calculation assumes a uniform beam intensity profile. You must now adjust this energy density to account for hotspots or other nonuniform intensity profiles and roughly calculate a maximum energy density. For reference a Gaussian beam typically has a maximum energy density that is twice that of the $1/e^2$ beam.

Now compare the maximum energy density to that which is specified as the LIDT for the optic. If the optic was tested at a wavelength other than your operating wavelength, the damage threshold must be scaled appropriately [3]. A good rule of thumb is that the damage threshold has an inverse square root relationship with wavelength such that as you move to shorter wavelengths, the damage threshold decreases (i.e., a LIDT of $1 \text{ J}/\text{cm}^2$ at 1064 nm scales to $0.7 \text{ J}/\text{cm}^2$ at 532 nm):

$$\text{Adjusted LIDT} = \text{LIDT Energy} \sqrt{\frac{\text{Your Wavelength}}{\text{LIDT Wavelength}}}$$

You now have a wavelength-adjusted energy density, which you will use in the following step.

Beam diameter is also important to know when comparing damage thresholds. While the LIDT, when expressed in units of J/cm^2 , scales independently of spot



LIDT in energy density vs. pulse length and spot size. For short pulses, energy density becomes a constant with spot size. This graph was obtained from [1].

size; large beam sizes are more likely to illuminate a larger number of defects which can lead to greater variances in the LIDT [4]. For data presented here, a <1 mm beam size was used to measure the LIDT. For beams sizes greater than 5 mm, the LIDT (J/cm²) will not scale independently of beam diameter due to the larger size beam exposing more defects.

The pulse length must now be compensated for. The longer the pulse duration, the more energy the optic can handle. For pulse widths between 1 - 100 ns, an approximation is as follows:

$$\text{Adjusted LIDT} = \text{LIDT Energy} \sqrt{\frac{\text{Your Pulse Length}}{\text{LIDT Pulse Length}}}$$

Use this formula to calculate the Adjusted LIDT for an optic based on your pulse length. If your maximum energy density is less than this adjusted LIDT maximum energy density, then the optic should be suitable for your application. Keep in mind that this calculation is only used for pulses between 10⁻⁹ s and 10⁻⁷ s. For pulses between 10⁻⁷ s and 10⁻⁴ s, the CW LIDT must also be checked before deeming the optic appropriate for your application.

Please note that we have a buffer built in between the specified damage thresholds online and the tests which we have done, which accommodates variation between batches. Upon request, we can provide individual test information and a testing certificate. Contact Tech Support for more information.

[1] R. M. Wood, Optics and Laser Tech. **29**, 517 (1998).

[2] Roger M. Wood, *Laser-Induced Damage of Optical Materials* (Institute of Physics Publishing, Philadelphia, PA, 2003).

[3] C. W. Carr *et al.*, Phys. Rev. Lett. **91**, 127402 (2003).

[4] N. Bloembergen, Appl. Opt. **12**, 661 (1973).

[Hide LIDT Calculations](#)

LIDT CALCULATIONS

In order to illustrate the process of determining whether a given laser system will damage an optic, a number of example calculations of laser induced damage threshold are given below. For assistance with performing similar calculations, we provide a spreadsheet calculator that can be downloaded by clicking the button to the right. To use the calculator, enter the specified LIDT value of the optic under consideration and the relevant parameters of your laser system in the green boxes. The spreadsheet will then calculate a linear power density for CW and pulsed systems, as well as an energy density value for pulsed systems. These values are used to calculate adjusted, scaled LIDT values for the optics based on accepted scaling laws. This calculator assumes a Gaussian beam profile, so a correction factor must be introduced for other beam shapes (uniform, etc.). The LIDT scaling laws are determined from empirical relationships; their accuracy is not guaranteed. Remember that absorption by optics or coatings can significantly reduce LIDT in some spectral regions. These LIDT values are not valid for ultrashort pulses less than one nanosecond in duration.


[LIDT Calculator](#)

CW Laser Example

Suppose that a CW laser system at 1319 nm produces a 0.5 W Gaussian beam that has a 1/e² diameter of 10 mm. A naive calculation of the average linear power density of this beam would yield a value of 0.5 W/cm, given by the total power divided by the beam diameter:

$$\text{Linear Power Density} = \frac{\text{Power}}{\text{Beam Diameter}}$$

However, the maximum power density of a Gaussian beam is about twice the maximum power density of a uniform beam, as shown in the graph to the right. Therefore, a more accurate determination of the maximum linear power density of the system is 1 W/cm.



A Gaussian beam profile has about twice the maximum intensity of a uniform beam profile.

An AC127-030-C achromatic doublet lens has a specified CW LIDT of 350 W/cm, as tested at 1550 nm. CW damage threshold values typically scale directly with the wavelength of the laser source, so this yields an adjusted LIDT value:

$$\text{Adjusted LIDT} = \text{LIDT Power} \left(\frac{\text{Your Wavelength}}{\text{LIDT Wavelength}} \right)$$

The adjusted LIDT value of 350 W/cm x (1319 nm / 1550 nm) = 298 W/cm is significantly higher than the calculated maximum linear power density of the laser system, so it would be safe to use this doublet lens for this application.

Pulsed Nanosecond Laser Example: Scaling for Different Pulse Durations

Suppose that a pulsed Nd:YAG laser system is frequency tripled to produce a 10 Hz output, consisting of 2 ns output pulses at 355 nm, each with 1 J of

energy, in a Gaussian beam with a 1.9 cm beam diameter ($1/e$). The average energy density of each pulse is found by dividing the pulse energy by the beam area:

$$\text{Energy Density} = \frac{\text{Pulse Energy}}{\text{Beam Area}}$$

As described above, the maximum energy density of a Gaussian beam is about twice the average energy density. So, the maximum energy density of this beam is $\sim 0.7 \text{ J/cm}^2$.

The energy density of the beam can be compared to the LIDT values of 1 J/cm^2 and 3.5 J/cm^2 for a BB1-E01 broadband dielectric mirror and an NB1-K08 Nd:YAG laser line mirror, respectively. Both of these LIDT values, while measured at 355 nm, were determined with a 10 ns pulsed laser at 10 Hz. Therefore, an adjustment must be applied for the shorter pulse duration of the system under consideration. As described on the previous tab, LIDT values in the nanosecond pulse regime scale with the square root of the laser pulse duration:

$$\text{Adjusted LIDT} = \text{LIDT Energy} \sqrt{\frac{\text{Your Pulse Length}}{\text{LIDT Pulse Length}}}$$

This adjustment factor results in LIDT values of 0.45 J/cm^2 for the BB1-E01 broadband mirror and 1.6 J/cm^2 for the Nd:YAG laser line mirror, which are to be compared with the 0.7 J/cm^2 maximum energy density of the beam. While the broadband mirror would likely be damaged by the laser, the more specialized laser line mirror is appropriate for use with this system.

Pulsed Nanosecond Laser Example: Scaling for Different Wavelengths

Suppose that a pulsed laser system emits 10 ns pulses at 2.5 Hz, each with 100 mJ of energy at 1064 nm in a 16 mm diameter beam ($1/e^2$) that must be attenuated with a neutral density filter. For a Gaussian output, these specifications result in a maximum energy density of 0.1 J/cm^2 . The damage threshold of an NDUV10A Ø25 mm, OD 1.0, reflective neutral density filter is 0.05 J/cm^2 for 10 ns pulses at 355 nm, while the damage threshold of the similar NE10A absorptive filter is 10 J/cm^2 for 10 ns pulses at 532 nm. As described on the previous tab, the LIDT value of an optic scales with the square root of the wavelength in the nanosecond pulse regime:

$$\text{Adjusted LIDT} = \text{LIDT Energy} \sqrt{\frac{\text{Your Wavelength}}{\text{LIDT Wavelength}}}$$

This scaling gives adjusted LIDT values of 0.08 J/cm^2 for the reflective filter and 14 J/cm^2 for the absorptive filter. In this case, the absorptive filter is the best choice in order to avoid optical damage.





Pulsed Microsecond Laser Example














Consider a laser system that produces 1 μs pulses, each containing 150 μJ of energy at a repetition rate of 50 kHz, resulting in a relatively high duty cycle of 5%. This system falls somewhere between the regimes of CW and pulsed laser induced damage, and could potentially damage an optic by mechanisms associated with either regime. As a result, both CW and pulsed LIDT values must be compared to the properties of the laser system to ensure safe operation.

If this relatively long-pulse laser emits a Gaussian 12.7 mm diameter beam ($1/e^2$) at 980 nm, then the resulting output has a linear power density of 5.9 W/cm and an energy density of $1.2 \times 10^{-4} \text{ J/cm}^2$ per pulse. This can be compared to the LIDT values for a WPQ10E-980 polymer zero-order quarter-wave plate, which are 5 W/cm for CW radiation at 810 nm and 5 J/cm^2 for a 10 ns pulse at 810 nm. As before, the CW LIDT of the optic scales linearly with the laser wavelength, resulting in an adjusted CW value of 6 W/cm at 980 nm. On the other hand, the pulsed LIDT scales with the square root of the laser wavelength and the square root of the pulse duration, resulting in an adjusted value of 55 J/cm^2 for a 1 μs pulse at 980 nm. The pulsed LIDT of the optic is significantly greater than the energy density of the laser pulse, so individual pulses will not damage the wave plate. However, the large average linear power density of the laser system may cause thermal damage to the optic, much like a high-power CW beam.

[Hide Ø1/2" \(12.7 mm\) Unmounted NIR ND Filters](#)

Ø1/2" (12.7 mm) Unmounted NIR ND Filters


Item #	Substrate (Schott)	Substrate Thickness ^a	Optical Density at 1064 nm ^{b,c}	Transmission at 1064 nm ^{b,c}	Optical Density at 1550 nm ^b	Transmission at 1550 nm ^b	Transmission Data ^d
NENIR501B	NG11	0.5 mm	0.14	72.44%	0.09	81.28%	
NENIR502B	NG11	1.2 mm	0.28	52.48%	0.16	69.18%	
NENIR503B	KG2	0.5 mm	0.38	41.69%	0.29	51.29%	
NENIR504B	KG2	0.6 mm	0.43	37.15%	0.39	40.74%	

NENIR505B	KG2	0.8 mm	0.53	29.51%	0.47	33.88%	
NENIR506B	KG2	1.0 mm	0.65	22.39%	0.58	26.30%	
NENIR507B	KG2	1.1 mm	0.74	18.20%	0.68	20.89%	
NENIR508B	KG2	1.3 mm	0.85	14.13%	0.77	16.98%	
NENIR509B	KG2	1.4 mm	0.96	10.96%	0.86	13.80%	
NENIR510B	KG2	1.6 mm	1.07	8.51%	0.94	11.48%	
NENIR513B	KG3	0.8 mm	1.41	3.89%	1.27	5.37%	
NENIR515B	KG3	1.0 mm	1.61	2.45%	1.44	3.63%	
NENIR520B	KG3	1.3 mm	2.14	0.72%	1.91	1.23%	
NENIR530B	KG3	2.0 mm	3.18	0.07%	2.87	0.13%	
NENIR540B	KG3	2.6 mm	4.13	0.007%	3.84	0.01%	
NENIR550B	KG5	2.3 mm	5.29	0.0005%	4.74	0.002%	
NENIR560B	KG5	2.8 mm	6.38	0.00004%	5.71	0.0002%	

a. Values given are typical. The actual thickness of each ND filter is dependent on the optical density of the lot of glass used to manufacture each lot of ND filters.

b. Optical density values are not exactly 0.5, 1.0, etc., at 1064 nm or 1550 nm in order to provide good performance at both wavelengths.











c. Values are typical.

d. Click on  for a plot and downloadable data.

Part Number	Description	Price	Availability
NENIR501B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.1	\$35.00	Today
NENIR502B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.2	\$35.00	Today
NENIR503B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.3	\$35.00	Today
NENIR504B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.4	\$35.00	Today
NENIR505B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.5	\$35.00	Today
NENIR506B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.6	\$35.00	Today
NENIR507B	Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.7	\$35.00	7-10 Days
NENIR508B	Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.8	\$35.00	Today
NENIR509B	Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 0.9	\$35.00	Today
NENIR510B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 1.0	\$35.00	Today
NENIR513B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 1.3	\$35.00	Today
NENIR515B	Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 1.5	\$35.00	Today
NENIR520B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 2.0	\$35.00	Today
NENIR530B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 3.0	\$35.00	Today
NENIR540B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 4.0	\$35.00	Today
NENIR550B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 5.0	\$35.00	Today
NENIR560B	Customer Inspired! Ø1/2" Unmounted NIR Absorptive ND Filter, OD: 6.0	\$35.00	Today

[Hide Ø25 mm Unmounted NIR ND Filters](#)

Ø25 mm Unmounted NIR ND Filters

Item #	Substrate (Schott)	Substrate Thickness ^a	Optical Density at 1064 nm ^{b,c}	Transmission at 1064 nm ^{b,c}	Optical Density at 1550 nm ^b	Transmission at 1550 nm ^b	Transmission Data ^d
NENIR01B	NG11	0.5 mm	0.14	72.44%	0.09	81.28%	
NENIR02B	NG11	1.2 mm	0.28	52.48%	0.16	69.18%	
NENIR03B	KG2	0.5 mm	0.32	47.86%	0.29	51.29%	
NENIR04B	KG2	0.6 mm	0.43	37.15%	0.39	40.74%	
NENIR05B	KG2	0.8 mm	0.53	29.51%	0.47	33.88%	
NENIR06B	KG2	1.0 mm	0.65	22.39%	0.58	26.30%	
NENIR07B	KG2	1.1 mm	0.74	18.20%	0.68	20.89%	
NENIR08B	KG2	1.3 mm	0.85	14.13%	0.77	16.98%	
NENIR09B	KG2	1.4 mm	0.96	10.96%	0.86	13.80%	
NENIR10B	KG2	1.6 mm	1.07	8.51%	0.94	11.48%	

NENIR13B	KG3	0.8 mm	1.41	3.89%	1.27	5.37%	
NENIR15B	KG3	1.0 mm	1.61	2.45%	1.44	3.63%	
NENIR20B	KG3	1.3 mm	2.14	0.72%	1.91	1.23%	
NENIR30B	KG3	2.0 mm	3.18	0.07%	2.87	0.13%	
NENIR40B	KG3	2.6 mm	4.13	0.007%	3.84	0.01%	
NENIR50B	HA5	2.3 mm	5.29	0.0005%	4.74	0.002%	
NENIR60B	HA5	2.8 mm	6.38	0.00004%	5.71	0.0002%	

a. Values given are typical. The actual thickness of each ND filter is dependent on the optical density of the lot of glass used to manufacture each lot of ND filters.

b. Optical density values are not exactly 0.5, 1.0, etc., at 1064 nm or 1550 nm in order to provide good performance at both wavelengths.














c. Values are typical.

d. Click on  for a plot and downloadable data.


Part Number	Description	Price	Availability
NENIR01B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.1	\$49.00	Today
NENIR02B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.2	\$49.00	Today
NENIR03B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.3	\$49.00	Today
NENIR04B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.4	\$49.00	7-10 Days
NENIR05B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.5	\$49.00	Today
NENIR06B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.6	\$49.00	Today
NENIR07B	Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.7	\$49.00	Today
NENIR08B	Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.8	\$49.00	Today
NENIR09B	Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 0.9	\$49.00	Today
NENIR10B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 1.0	\$49.00	Today
NENIR13B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 1.3	\$49.00	Today
NENIR15B	Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 1.5	\$49.00	Today
NENIR20B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 2.0	\$49.00	Today
NENIR30B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 3.0	\$49.00	Today
NENIR40B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 4.0	\$49.00	Today
NENIR50B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 5.0	\$49.00	Today
NENIR60B	Customer Inspired! Ø25 mm Unmounted NIR Absorptive ND Filter, OD: 6.0	\$49.00	Today

[Hide 2" Square Unmounted NIR ND Filters](#)

2" Square Unmounted NIR ND Filters

Item #	Substrate (Schott)	Substrate Thickness ^a	Optical Density at 1064 nm ^{b,c}	Transmission at 1064 nm ^{b,c}	Optical Density at 1550 nm ^b	Transmission at 1550 nm ^b	Transmission Data ^d
NENIR201B	NG11	0.5 mm	0.14	72.44%	0.09	81.28%	
NENIR202B	NG11	1.2 mm	0.28	52.48%	0.16	69.18%	
NENIR203B	KG2	0.5 mm	0.32	47.86%	0.29	51.29%	
NENIR204B	KG2	0.6 mm	0.43	37.15%	0.39	40.74%	
NENIR205B	KG2	0.8 mm	0.53	29.51%	0.47	33.88%	
NENIR206B	KG2	1.0 mm	0.65	22.39%	0.58	26.30%	
NENIR207B	KG2	1.1 mm	0.74	18.20%	0.68	20.89%	
NENIR208B	KG2	1.3 mm	0.85	14.13%	0.77	16.98%	
NENIR209B	KG2	1.4 mm	0.96	10.96%	0.86	13.80%	
NENIR210B	KG2	1.6 mm	1.07	8.51%	0.94	11.48%	
NENIR213B	KG3	0.8 mm	1.41	3.89%	1.27	5.37%	
NENIR215B	KG3	1.0 mm	1.61	2.45%	1.44	3.63%	
NENIR220B	KG3	1.3 mm	2.14	0.72%	1.91	1.23%	
NENIR230B	KG3	2.0 mm	3.18	0.07%	2.87	0.13%	
NENIR240B	KG3	2.6 mm	4.13	0.007%	3.84	0.01%	
NENIR250B	HA5	2.3 mm	5.29	0.0005%	4.74	0.002%	

NENIR260B	HA5	2.8 mm	6.38	0.00004%	5.71	0.0002%	
-----------	-----	--------	------	----------	------	---------	---

- Values given are typical. The actual thickness of each ND filter is dependent on the optical density of the lot of glass used to manufacture each lot of ND filters.
- Optical density values are not exactly 0.5, 1.0, etc., at 1064 nm or 1550 nm in order to provide good performance at both wavelengths.
- Values are typical.
- Click on  for a plot and downloadable data.

Part Number	Description	Price	Availability
NENIR201B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.1	\$87.00	Today
NENIR202B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.2	\$87.00	Today
NENIR203B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.3	\$87.00	Today
NENIR204B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.4	\$87.00	7-10 Days
NENIR205B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.5	\$87.00	Today
NENIR206B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.6	\$87.00	Today
NENIR207B	2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.7	\$87.00	Today
NENIR208B	2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.8	\$87.00	Today
NENIR209B	2" x 2" Unmounted NIR Absorptive ND Filter, OD: 0.9	\$87.00	Today
NENIR210B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 1.0	\$87.00	Today
NENIR213B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 1.3	\$87.00	Today
NENIR215B	2" x 2" Unmounted NIR Absorptive ND Filter, OD: 1.5	\$87.00	Today
NENIR220B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 2.0	\$87.00	Today
NENIR230B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 3.0	\$87.00	Today
NENIR240B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 4.0	\$87.00	Today
NENIR250B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 5.0	\$87.00	Today
NENIR260B	Customer Inspired! 2" x 2" Unmounted NIR Absorptive ND Filter, OD: 6.0	\$87.00	Today

Graphs

The shaded regions in the graphs below denote the wavelength range over which we recommend using this filter; and the dotted line denotes the filter's designated optical density. To view an excel file that lists all of the measured transmission values for this filter from 200 nm to 16 μm, please click [here](#).

